

CLAIMS:

1. A method for molding a replica, comprising the steps of forming a mother mold from a transparent cured product of a photo-curable liquid silicone rubber composition, the mother mold having a cavity corresponding to the outer contour of an article to be duplicated, filling the mold cavity with a photo-curable liquid resin, and irradiating light to the photo-curable liquid resin from outside the mother mold, thereby curing the photo-curable liquid resin within the mother mold to produce a replica.
2. A method for molding a replica, comprising the steps of (a) filling a container having at least one light-transmissive side surface with a photo-curable liquid silicone rubber composition, submerging a master model in the liquid silicone rubber composition, and irradiating light to the liquid silicone rubber composition to cure the composition to form a transparent silicone rubber part having the master model embedded therein, (b) cutting the silicone rubber part into sections and removing the master model therefrom, the sections when mated constituting a silicone rubber mother mold having a cavity corresponding to the outer contour of the master model, (c) mating the sections of the silicone rubber mother mold, filling the cavity with a photo-curable liquid resin, and irradiating light to the photo-curable liquid resin from outside the mother mold, thereby curing the photo-curable liquid resin within the mother mold to produce a replica, (d) removing the replica from the silicone rubber mother mold.
3. The method of claim 2 wherein the master model is produced by an optical shaping process of irradiating light to a photo-curable liquid resin composition on the basis of CAD data regarding the shape and dimensions of the master

model designed by three-dimensional CAD technique, thereby curing the resin composition.

4. The method of claim 1 wherein the irradiated light has  
5 a wavelength in the range of 200 to 500 nm.

5. The method of claim 2 wherein the irradiated light has a wavelength in the range of 200 to 500 nm.

10 6. An apparatus for molding a replica comprising  
a mother mold having a cavity corresponding to the  
outer contour of an article to be duplicated, said mother  
mold being formed from a transparent cured product of a  
photo-curable composition,  
15 a means for casting or filling the mold cavity with a  
photo-curable liquid resin, and  
a means for irradiating light to the photo-curable  
liquid resin from outside the mother mold thereby curing the  
photo-curable resin.

20 7. The apparatus of claim 6 wherein said mother mold is  
formed from a transparent cured product of a photo-curable  
liquid silicone rubber composition.

25 8. The apparatus of claim 6 wherein said casting means  
includes a means for agitating and defoaming said photo-  
curable liquid resin under a reduced pressure.

*is vacuum*

30 9. The apparatus of claim 6 wherein said light irradiating  
means irradiates light having a wavelength in the range of  
200 to 500 nm.